

to
wels


TOWELS





TOWELS






Towels



FABRIC CODE :

CHECKERBOARD



**FABRIC SPECIFICATION SHEET /
HOJA DE ESPECIFICACIÓN DE TELAS**

Fabric Name / Artículo	TOWEL CHECKERBOARD BATH
#Pattern / #Patrón	T 521
Final width / Ancho acabado	27.0 ± 1.0 inch
Final lenght / Largo acabado	56.0 ± 1.0 inch
Yarn Numbering / Título de hilos	10.0/1 + 10.0/1 x 12.0/1 ± 10.0%
Fiber content / Composición	77.0%Co. - 23.0%Poli. ± 3.0%
Weight by docen / Peso docena	18.2 lb
Curl Height / Altura de rizo	1x6.0
Origin / Lugar de origen	GUATEMALA, CENTROAMERICA

Finish / Acabado	Regular
Date / Fecha	Junio 18, 2020

24/06/2020

The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.

Basado en Norma ASTM D5433-00
Preparado por: Pedro Pablo Ng

SUGGESTED CARE INSTRUCTIONS:

Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.



☎ PBX: (502) 6633-6550
✉ Email: textil@liztex.com

Parques del Lago Km. 30.5 Carretera al Pacífico.
Amatitlán, Guatemala, Guatemala.

TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Tensile Strength / Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
Dimensional Change / Estabilidad Dimensional	AATCC 135 1-III -AI 3 cycles	±10.0% x ±4.0%	
Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cycles	Acceptable	
Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
Color change / Cambio de color	AATCC 61 - 2001 - 2A		
Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
	ACETATE	3.0 min	
	COTTON	3.0 min	
	NYLON	3.0 min	
	POLYESTER	3.0 min	
	ACRILIC	3.0 min	
	WOOL	3.0 min	
Composition / Composición	AATCC 20 - 2000 - IV	77.0%Co. - 23.0%Poli.	
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.  PBX: (502) 6633-6550 Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL CHECKERBOARD HAND #Pattern / #Patrón T 520 Finished widht / Ancho acabado 16.0 ± 1.0 inch Finished lenght / Largo acabado 26.0 ± 1.0 inch Threads title / Título de hilos 10.0/1 + 12.0/1 x 12.0/1+ 22.0/2 ± 10.0% Composition / Composición 72.0%Co. - 28.0%Poli. ± 3.0% Weight by docen / Peso docena 4 lb Curl Height / Altura de rizo 1x4.2 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile strength / Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional stability / Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Post Wash Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Rub solidity / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Wash/stain fastness / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
Finish / Acabado Regular Date / Fecha Junio 18, 2020 24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.			POLIESTER	3.0 min	
			ACRILIC	3.0 min	
			WOOL	3.0 min	
		Composition / Composición	AATCC 20 - 2000 - IV	72.0%Co. - 28.0%Poli.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.			
		litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

Hand

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL CHECKERBOARD BATH MAT #Pattern / #Patrón T 519 Final width / Ancho acabado 20.0 ± 1.0 inch Final lenght / Largo acabado 32.0 ± 1.0 inch Yarn Numbering / Título de hilos 12.0/1 + 6.0/1 x 12.0/1 ± 10.0% Fiber content / Composición 882.0%Co. - 18.0%Poli. ± 3.0% Weight by docen / Peso docena 9.2 lb Curl Height / Altura de rizo 1x4.6 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
Finish / Acabado Regular Date / Fecha Junio 18, 2020			POLIELSTER	3.0 min	
			ACRILIC	3.0 min	
			WOOL	3.0 min	
		Composition / Composición	AATCC 20 - 2000 - IV	82.0%Co. - 18.0%Poli.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.			
		24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.			
		litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			





FABRIC CODE :

SIENA



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL SIENA 28 x 58 BATH #Pattern / #Patrón T 510 Final width / Ancho acabado 28.0 ± 1.0 inch Final lenght / Largo acabado 58.0 ± 1.0 inch Yarn Numbering / Título de hilos 22.0/2 + 10.0/1 x 14.0/1+ 22.0/2 ± 10.0% Fiber content / Composición 87.0% Co. - 13.0%Poli. ± 3.0% Weight by docen / Peso docena 18.6 lb Curl Height / Altura de rizo 1x5.8 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
	POLYESTER	3.0 min			
	ACRILIC	3.0 min			
	WOOL	3.0 min			
Composition / Composición	AATCC 20 - 2000 - IV	87.0%Co. - 13.0%Poli.			
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White		
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		 PBX: (502) 6633-6550 Email: textil@litzex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

BATH

24/06/2020

The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.

Bath

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN		
Fabric Name / Artículo TOWEL SIENA 13 x 13 WASH #Pattern / #Patrón T 541 Final width / Ancho acabado 10.0 ± 1.0 inch Final lenght / Largo acabado 30.0 ± 1.0 inch Yarn Numbering / Título de hilos 10.0/1 + 12.0/1 x 12.0/1+ 22.0/2 ± 10.0% Fiber content / Composición 84.0%Co. - 16.0%Poli. ± 3.0% Weight by docen / Peso docena 1.6 lb Curl Height / Altura de rizo 1x5.2 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min		Bath
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%		
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable		
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors		
		Color change / Cambio de color	AATCC 61 - 2001 - 2A			
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4		
			ACETATE	3.0 min		
			COTTON	3.0 min		
			NYLON	3.0 min		
Finish / Acabado Regular Date / Fecha Junio 18, 2020 WASH 24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.						
		Composition / Composición	AATCC 20 - 2000 - IV	84.0%Co. - 16.0%Poli.		
Ph		AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White		
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		 PBX: (502) 6633-6550 Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.				

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS	
Fabric Name / Artículo	TOWEL SIENA 16 X 30 HAND
#Pattern / #Patrón	T 541
Final width / Ancho acabado	10.0 ± 1.0 inch
Final length / Largo acabado	30.0 ± 1.0 inch
Yarn Numbering / Título de hilos	10.0/1 + 12.0/1 x 12.0/1+ 22.0/2 ± 10.0%
Fiber content / Composición	84.0%Co. - 16.0%Poli. ± 3.0%
Weight by dozen / Peso docena	4.7 lb
Curl Height / Altura de rizo	1x5.2
Origin / Lugar de origen	GUATEMALA, CENTROAMERICA

Finish / Acabado	Regular
Date / Fecha	Junio 18, 2020



HAND

HAND

The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.

SUGGESTED CARE INSTRUCTIONS:



Parques del Lago Km. 30.5 Carretera al Pacífico.
Amatitlán, Guatemala, Guatemala.

TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
Color change / Cambio de color	AATCC 61 - 2001 - 2A		
Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
	ACETATE	3.0 min	
	COTTON	3.0 min	
	NYLON	3.0 min	
	POLIELSTER	3.0 min	
	ACRILIC	3.0 min	
	WOOL	3.0 min	
Composition / Composición	AATCC 20 - 2000 - IV	84.0%Co. - 16.0%Poli.	
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.  PBX: (502) 6633-6550 Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			




FABRIC CODE :

GENOA




CLICK



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN		
Fabric Name / Artículo TOWEL GENOA 30 x 60 BATH #Pattern / #Patrón #T 393 Final width / Ancho acabado 30.0 ± 1.0 inch Final lenght / Largo acabado 60.0 ± 1.0 inch Yarn Numbering / Título de hilos 22.0/2 + 22.0/2 x 12.0/1+ 22.0/2 ± 10.0% Fiber content / Composición 88.0% Co. - 12.0%Poli. ± 3.0% Weight by docen / Peso docena 24.5 lb Curl Height / Altura de rizo 1x7.8 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min		Bath
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%		
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable		
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors		
		Color change / Cambio de color	AATCC 61 - 2001 - 2A			
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4		
			ACETATE	3.0 min		
			COTTON	3.0 min		
			NYLON	3.0 min		
	POLIESTER	3.0 min				
	ACRILIC	3.0 min				
	WOOL	3.0 min				
Composition / Composición	AATCC 20 - 2000 - IV	88.0% Cotton - 12.0%Polister				
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White			
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		litztex 📞 PBX: (502) 6633-6550 ✉ Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.				

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN		
Fabric Name / Artículo TOWEL GENOA 12 x 13 WASH #Pattern / #Patrón #T 397 Final width / Ancho acabado 12.0 ± 1.0 inch Final lenght / Largo acabado 13.0 ± 1.0 inch Yarn Numbering / Título de hilos 12.0/2 + 22.0/2 x 12.0/1+ 22.0/2 ± 10.0% Fiber content / Composición 88.0% Co. - 12.0%Poli. ± 3.0% Weight by docen / Peso docena 1.7 lb Curl Height / Altura de rizo 1x6.2 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min		Bath
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%		
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable		
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors		
		Color change / Cambio de color	AATCC 61 - 2001 - 2A			
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4		
			ACETATE	3.0 min		
			COTTON	3.0 min		
			NYLON	3.0 min		
Finish / Acabado Regular Date / Fecha Junio 18, 2020			POLIESTER	3.0 min		
			ACRILIC	3.0 min		
			WOOL	3.0 min		
		Composition / Composición	AATCC 20 - 2000 - IV	88.0% Cotton - 12.0%Polister		
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White	
Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.				

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN		
Fabric Name / Artículo TOWEL GENOA 16 x 29 HAND #Pattern / #Patrón #T 396 Final width / Ancho acabado 16.0 ± 1.0 inch Final lenght / Largo acabado 29.0 ± 1.0 inch Yarn Numbering / Título de hilos 22.0/2 + 22.0/2 x 12.0/1+ 22.0/2 ± 10.0% Fiber content / Composición 88.0% Co. - 12.0%Poli. ± 3.0% Weight by docen / Peso docena 6.5 lb Curl Height / Altura de rizo 1x8.2 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min		Bath
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%		
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable		
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors		
		Color change / Cambio de color	AATCC 61 - 2001 - 2A			
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4		
			ACETATE	3.0 min		
			COTTON	3.0 min		
			NYLON	3.0 min		
Finish / Acabado Regular Date / Fecha Junio 18, 2020			POLIESTER	3.0 min		
			ACRILIC	3.0 min		
			WOOL	3.0 min		
		Composition / Composición	AATCC 20 - 2000 - IV	88.0% Cotton - 12.0%Polister		
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White	
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		litztex 📞 PBX: (502) 6633-6550 ✉ Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.				




Towels



FABRIC CODE :

SAILOR STRIPE




FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN																			
<table><tr><td>Fabric Name / Artículo</td><td>TOWEL SAILOR STRIPE 30 x 60</td></tr><tr><td>#Pattern / #Patrón</td><td>T 436, 437, 454, 455 y 456</td></tr><tr><td>Final width / Ancho acabado</td><td>30.0 ± 1.0 inch</td></tr><tr><td>Final lenght / Largo acabado</td><td>60.0 ± 1.0 inch</td></tr><tr><td>Yarn Numbering / Título de hilos</td><td>12.0/1 + 16.0/1 x 12.0/1 +300/72 ± 10.0%</td></tr><tr><td>Fiber content / Composición</td><td>77.0%A Co. - 23.0%Poli. ± 3.0%</td></tr><tr><td>Weight by docen / Peso docena</td><td>13.2 lb</td></tr><tr><td>Curl Height / Altura de rizo</td><td>1x5.0</td></tr><tr><td>Origin / Lugar de origen</td><td>GUATEMALA, CENTROAMERICA</td></tr></table>		Fabric Name / Artículo	TOWEL SAILOR STRIPE 30 x 60	#Pattern / #Patrón	T 436, 437, 454, 455 y 456	Final width / Ancho acabado	30.0 ± 1.0 inch	Final lenght / Largo acabado	60.0 ± 1.0 inch	Yarn Numbering / Título de hilos	12.0/1 + 16.0/1 x 12.0/1 +300/72 ± 10.0%	Fiber content / Composición	77.0%A Co. - 23.0%Poli. ± 3.0%	Weight by docen / Peso docena	13.2 lb	Curl Height / Altura de rizo	1x5.0	Origin / Lugar de origen	GUATEMALA, CENTROAMERICA	Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Fabric Name / Artículo	TOWEL SAILOR STRIPE 30 x 60																				
		#Pattern / #Patrón	T 436, 437, 454, 455 y 456																				
		Final width / Ancho acabado	30.0 ± 1.0 inch																				
		Final lenght / Largo acabado	60.0 ± 1.0 inch																				
		Yarn Numbering / Título de hilos	12.0/1 + 16.0/1 x 12.0/1 +300/72 ± 10.0%																				
		Fiber content / Composición	77.0%A Co. - 23.0%Poli. ± 3.0%																				
		Weight by docen / Peso docena	13.2 lb																				
		Curl Height / Altura de rizo	1x5.0																				
		Origin / Lugar de origen	GUATEMALA, CENTROAMERICA																				
Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%																					
Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable																					
Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors																					
Color change / Cambio de color	AATCC 61 - 2001 - 2A																						
Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4																					
	ACETATE	3.0 min																					
	COTTON	3.0 min																					
	NYLON	3.0 min																					
	POLIESTER	3.0 min																					
	ACRILIC	3.0 min																					
	WOOL	3.0 min																					
Composition / Composición	AATCC 20 - 2000 - IV	77.0% Co. - 23.0%Poli.																					
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White																				
24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.		litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.																					
						Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.																	

Sailor Towel Color Card




T437



T454



T456




T436


Sailor Towel Color Card



T603



T571




T495





FABRIC CODE :

COSMO POOL



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL COSMO POOL 66 X 38 #Pattern / #Patrón T 478 Finished widht / Ancho acabado 38.0 ± 1.0 inch Finished lenght / Largo acabado 66.0 ± 1.0 inch Threads title / Título de hilos 10.0/1 + 16.0/1 x 12.0/1 +300/72 fil tex ± 10.0% Composition / Composición 81.0%Co. - 19.0%PES /Poli. ± 3.0% Weight by docen / Peso docena 24 lb Curl Height / Altura de rizo 1x6.3 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb mín	
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	10.0% x 6.0% max	
		Appeareance /Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Crocking /Solidez al Frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Staining /Solidez al Lavado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
Finish / Acabado Regular Date / Fecha Junio 24, 2020 Rev No. 1			POLIELSTER	3.0 min	
			ACRILIC	3.0 min	
			WOOL	3.0 min	
		Fiber content /Composición	AATCC 20 - 2000 - IV	81.0%Co. - 19.0%PES/Poli.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm. litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			
24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.					





FABRIC CODE :

PALAZZO



CLICK




FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN		
Fabric Name / Artículo TOWEL PALAZZO 35x70 BATH #Pattern / #Patrón T 420 Final width / Ancho acabado 35.0 ± 1.0 inch Final lenght / Largo acabado 70.0 ± 1.0 inch Yarn Numbering / Título de hilos 12.0/1 + 22.0/1 x 12/1+ 330/72 ± 10.0% Fiber content / Composición 83.0%Co. - 17.0%Poli. ±3.0% Weight by docen / Peso docena 23.8 lb Curl Height / Altura de rizo 1x5.0 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min		Bath
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%		
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable		
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors		
		Color change / Cambio de color	AATCC 61 - 2001 - 2A			
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4		
			ACETATE	3.0 min		
			COTTON	3.0 min		
			NYLON	3.0 min		
Finish / Acabado Regular Date / Fecha Junio 18, 2020 BATH 24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.			POLIELSTER	3.0 min		
			ACRILIC	3.0 min		
			WOOL	3.0 min		
		Composition / Composición	AATCC 20 - 2000 - IV	83.0%Co. - 17.0%Poli.		
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White	
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		litztex 📞 PBX: (502) 6633-6550 ✉ Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.		

Palazzo Towel Color Card



T392




T420



T398





Towels



FABRIC CODE:

ROXI PATTERNED



litzex




**FABRIC SPECIFICATION SHEET /
HOJA DE ESPECIFICACIÓN DE TELAS**

TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN
---------------	----------------------	--------------------------------



Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
Color change / Cambio de color	AATCC 61 - 2001 - 2A		
Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
	ACETATE	3.0 min	
	COTTON	3.0 min	
	NYLON	3.0 min	
	POLYESTER	3.0 min	
	ACRILIC	3.0 min	
	WOOL	3.0 min	
Composition / Composición	AATCC 20 - 2000 - IV	87.0%Co. - 13.0%Poli.	
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White


Bath

Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.	 ☎ PBX: (502) 6633-6550 ✉ Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.
--	--



FABRIC CODE :

HOLIDAY STRIPE



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL HOLIDAY STRIPE 30 x 60 #Pattern / #Patrón T 482, 549, 562, 611 a 616 Finished widht / Ancho acabado 30.0 ± 1.0 inch Finished lenght / Largo acabado 60.0 ± 1.0 inch Threads title / Título de hilos 12.0/1 + 12.0/1 x 12.0/1 + 22/2 ± 10.0% Composition / Composición 100.0% Co. Weight by docen / Peso docena 11.4 lb Curl Height / Altura de rizo 1x4.0 Origin / Lugar de origen GUATEMALA, CENTROAMERICA	Tensile strength / Resistencia a la Tensión		ASTM D 5034-95	40.0 lb x 30.0 lb min	
	Dimensional stability / Estabilidad Dimensional		AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
	Post Wash Appearance / Apariencia Post Lavado		AATCC 135 1-III -AI 3 cicles	Acceptable	
	Rub solidity / Solidez al frote		AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
	Color change / Cambio de color		AATCC 61 - 2001 - 2A		
	Wash/stain fastness / Solidez al Lavado/manchado		AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
		POLIESTER	3.0 min		
		ACRILIC	3.0 min		
		WOOL	3.0 min		
Composition / Composición		AATCC 20 - 2000 - IV	100% Cotton		
Ph		AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White	
24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.  PBX: (502) 6633-6550 Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

Holiday Towel Color Card




T612



T611



T615



T614



Holiday Towel Color Card



T613



T616





FABRIC CODE:

BEN STRIPE



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL BEN STRIPE 30x60 #Pattern / #Patrón T 622, 626, 627 y 628 Finished widht / Ancho acabado 30.0 ± 1.0 inch Finished lenght / Largo acabado 60.0 ± 1.0 inch Threads title / Título de hilos 12.0/1 + 12.0/1 x 12.0/1+ 20/2 ± 10.0% Composition / Composición 100%Co. Weight by docen / Peso docena 14 lb Curl Height / Altura de rizo 1x4.8 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile strength / Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional stability / Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Post Wash Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Rub solidity / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Wash/stain fastness / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
Finish / Acabado Regular Date / Fecha Junio 18, 2020 24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.			POLIESTER	3.0 min	
			ACRILIC	3.0 min	
			WOOL	3.0 min	
		Composition / Composición	AATCC 20 - 2000 - IV	100% Co.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.			
		 PBX: (502) 6633-6550 Email: textil@litzex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala. Bath			

Ben Stripe Towel Color Card



T626



T628



T627



T622





FABRIC CODE :

VALERIE



CLICK



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL VALERIE 30 x 60 BATH #Pattern / #Patrón T 446 Finished widht / Ancho acabado 30.0 ± 1.0 inch Finished lenght / Largo acabado 60.0 ± 1.0 inch Threads title / Título de hilos 12.0/1 + 12.0/1 x 12.0/1 + 12.0/1 ± 10.0% Composition / Composición 100.0%Co. Weight by docen / Peso docena 11.5 lb Curl Height / Altura de rizo 1x4.0 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile strength / Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional stability / Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Post Wash Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Rub solidity / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Wash/stain fastness / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
	POLIELSTER	3.0 min			
	ACRILIC	3.0 min			
	WOOL	3.0 min			
Composition / Composición	AATCC 20 - 2000 - IV	100.0%Co.			
Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White		
Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.		litztex PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

BATH

24/06/2020

The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.

Bath




FABRIC CODE:

SAUL STRIPE

litzex

FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL BEN STRIPE 30x60 #Pattern / #Patrón T 622, 626, 627 y 628 Finished widht / Ancho acabado 30.0 ± 1.0 inch Finished lenght / Largo acabado 60.0 ± 1.0 inch Threads title / Título de hilos 12.0/1 + 12.0/1 x 12.0/1+ 20/2 ± 10.0% Composition / Composición 100%Co. Weight by docen / Peso docena 14 lb Curl Height / Altura de rizo 1x4.8 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile strength / Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional stability / Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Post Wash Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Rub solidity / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Wash/stain fastness / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
Finish / Acabado Regular Date / Fecha Junio 18, 2020 24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.			POLIESTER	3.0 min	
			ACRILIC	3.0 min	
			WOOL	3.0 min	
		Composition / Composición	AATCC 20 - 2000 - IV	100% Co.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.			
		 PBX: (502) 6633-6550 Email: textil@liztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			


Saul Towel Color Card



T620



T621



T619



T629





FABRIC CODE :


OCEAN STRIPE



FABRIC SPECIFICATION SHEET / HOJA DE ESPECIFICACIÓN DE TELAS		TEST / PRUEBA	TEST METHOD / MÉTODO	SPECIFICATION / ESPECIFICACIÓN	
Fabric Name / Artículo TOWEL OCEAN STRIPE 30x60 #Pattern / #Patrón T 578 a 582 Final width / Ancho acabado 33.0 ± 1.0 inch Final lenght / Largo acabado 66.0 ± 1.0 inch Yarn Numbering / Título de hilos 12.0/1 + 12.0/1 x 12.0/1 ± 10.0% Fiber content / Composición 100%Co. Weight by docen / Peso docena 12 lb Curl Height / Altura de rizo 1x5.0 Origin / Lugar de origen GUATEMALA, CENTROAMERICA		Tensile Strength /Resistencia a la Tensión	ASTM D 5034-95	40.0 lb x 30.0 lb min	
		Dimensional Change /Estabilidad Dimensional	AATCC 135 1-III -AI 3 cicles	±10.0% x ±4.0%	
		Appearance / Apariencia Post Lavado	AATCC 135 1-III -AI 3 cicles	Acceptable	
		Crocking / Solidez al frote	AATCC 8 - 1995	Damp 3.0 min and Dry 4.0 min 2.0 and 3.0 for dark colors	
		Color change / Cambio de color	AATCC 61 - 2001 - 2A		
		Staining / Solidez al Lavado/manchado	AATCC 61 - 2001 - 2A	4	
			ACETATE	3.0 min	
			COTTON	3.0 min	
			NYLON	3.0 min	
		POLIESTER	3.0 min		
		ACRILIC	3.0 min		
		WOOL	3.0 min		
		Composition / Composición	AATCC 20 - 2000 - IV	100% Co.	
		Ph	AATCC 81 - 2001	5.0 a 8.0	4.0 a 6.5 for White
24/06/2020 The information provided in this document is given in good faith and is true and accurate to the best of our knowledge; There is no express or implicit guarantee on the accuracy of such data. It is the responsibility of the user to determine the convenience for your own use of the information presented.		Basado en Norma ASTM D5433-00 Preparado por: Pedro Pablo Ng SUGGESTED CARE INSTRUCTIONS: Machine wash cold; Wash with like colors; Remove from the washing machine immediately; Bleach without chlorine if necessary; Machine dry warm.  PBX: (502) 6633-6550 Email: textil@litztex.com Parques del Lago Km. 30.5 Carretera al Pacífico. Amatitlán, Guatemala, Guatemala.			

Bath


Ocean Towel Color Card



T582



T578




T580



T579

Ocean Towel Color Card



T581



Towel

☎ PBX: (502) 6633-6550
✉ Email: textil@liztex.com

Parques del Lago Km. 30.5 Carretera al Pacífico.
Amatitlán, Guatemala, Guatemala.

