



TECHNICAL DATA SHEET

Z8

RECOMMENDATIONS

Automotive
Other paint protection surface

SPECIFICATIONS

Test items	Test methods	Test values and descriptions
Appearance	Visual	The roll is smooth without wrinkles, flow marks, gel and crease
TPU base film	Thickness tester	150μm
TOPCOAT+base film+PSA	Thickness Tester	190±3μm
Width	Tape measure	1560±2mm
Length	Tape measure	15M
TOPCOAT	Thickness Tester	≥10μm
PSA	Thickness Tester	≥25μm
180° Peel force	Tensile tester	≥2000g

NOTE: THE ABOVE DATA IS BASED ON THE TEST RESULTS OF OUR LABORATORY.
DIFFERENT CONDITIONS RESULT IN VARYING VALUE.

PERFORMANCES

Test items	Test methods	Test values and descriptions
Heal performance	Steel brush, hot air blower	Fully recovered
Elongation at break/Horizontal	Tensile tester	≥350%
Vertical	Tensile tester	≥350%
Tensile strength at break/Horizontal	Tensile tester	≥25MPa
Vertical	Tensile tester	≥25MPa
Stain resistant	Shuang Jie marker, alcohol	Slight stain of color
Water drop angle	Water drop angle tester	Hydrophobic

NOTE: THE ABOVE DATA IS BASED ON THE TEST RESULTS OF OUR LABORATORY.
DIFFERENT CONDITIONS RESULT IN VARYING VALUE.

STORAGE

Paint Protection Film should be stored at room temperature, 59°F to 86°F (15°C to 30°C), and 40%-60% relative humidity. Film should be installed within one year of purchase.

WARRANTY

Z8 Paint Protective Film is warranted to be free of any manufacturing or workmanship defects for twelve (12) years from the date of purchase. The warranty does not cover damage caused by erroneous application, accidents or intentional misuse.

Disclaimer: The data in this publication is the result of careful research based on existing general theories, materials, techniques, experimental conditions, etc. (and is for informational purposes only), and may fluctuate due to storage time, storage conditions, and human factors. We do not rule out the possibility of modifying the properties displayed on product data and other technical data sheets based on future knowledge. We reserve the right to maintain the product name unchanged when future product parameters or features differing from existing product information. Regardless of whether the data provided in this publication fluctuates, any user is responsible for testing the applicability of this product for specific purposes and investigating the possibility of third-party intellectual property violations in the industry. Therefore, the information provided in this publication cannot be considered as a complete binding, guarantee, or assurance of product performance.