

JUNMA TYRE CORD COMPANY LIMITED

NO.80, CHENGHANG HEDONG ROAD, YANGSHE TOWN ZHANGJIAGANG CITY, JIANGSU PROVINCE CHINA

Nylon 66 Yarn for Air Big

Properties	210D/35F(235dtex)	420D/70F(470dtex)
Linear Density:dtex	235±15	470±15
Irregularity of Linear Density: %	≤ 1.5	≤ 1.5
Breaking Force:N	≥ 18.0	≥ 36.0
coefficient of variation of Breaking Force %	≤ 4.0	≤ 4.0
Elongation@4.7cN/dtex %	10.5±1.5	11.5±1.5
Elongation at break %	20.0±3.0	21.0±3.0
coefficient of variation of Elongation at break %	≤ 6.0	≤ 6.0
Hot Air Shrinkage % @177℃ *2Min*0.05cN/dtex	4.0±1.5	4.0±1.5
Heat Resistance@180℃ *4h %	≥ 90	≥ 90
Intermingling Points:number per meter	≥ 10	≥ 10
Finish Oil Content %	0.8±0.4	0.8±0.4

JUNMA TYRE CORD COMPANY LIMITED