

充气材料

Item 货号	Olympic	U1781G	I2161M	I1861G	Testing Method
Width 门幅	150 cm 59 inch	206 cm 81 inch	152 cm 60 inch	152 cm 60 inch	
Base Fabric 基布	100%PES 1100Dtex 20x20/inch	100%PES 1100Dtex 18x21/inch	100%PES 1100Dtex 18x17/inch	100%PES 1430Dtex 20x20/inch	DIN EN ISO 2060
Total Weight 总克重	610 g/m ² 18 OZ/YD ²	595 g/m ² 17.5 OZ/YD ²	700 g/m ² 20.6 OZ/YD ²	630 g/m ² 18.5 OZ/YD ²	DIN EN ISO 2286-2 BS 3424 Method 5A
Composition Fabric 基布克重	180 g/m ²	190 g/m ²	180 g/m ²	200 g/m ²	DIN EN ISO 2286-2 BS 3424 Method 5B
Composition Coating 涂层克重	5.3 OZ/YD ² 430 g/m ²	5.5 OZ/YD ² 405 g/m ²	5.3 OZ/YD ² 520 g/m ²	5.9 OZ/YD ² 430 g/m ²	
Lacquering (Optional) 表处 (可选)	Olympic	Gloss	Gloss	Gloss	
Breaking Strength Warp 抗拉强度 (经向)	2400 N/5cm 540 LBS/2inch	2600 N/5cm 585 LBS/2inch	2800 N/5cm 630 LBS/2inch	2600 N/5cm 585 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Breaking Strength Weft 抗拉强度 (纬向)	2200 N/5cm 495 LBS/2inch	2400 N/5cm 540 LBS/2inch	2600 N/5cm 585 LBS/2inch	2400 N/5cm 540 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Tear Strength Warp 撕裂强度 (经向)	250 N 56 LBS	500 N 110 LBS	450 N 100 LBS	400 N 90 LBS	DIN 53 363 BS 3424 Method FS 5134
Tear Strength Weft 撕裂强度 (纬向)	250 N 56 LBS	450 N 100 LBS	450 N 100 LBS	400 N 90 LBS	DIN 53 363 BS 3424 Method FS 5134
Adhesion 剥离强度	150 N/5cm 33 LBS/2inch	150 N/5cm 33 LBS/2inch	150 N/5cm 33 LBS/2inch	150 N/5cm 33 LBS/2inch	DIN 53 357 BS 3424 Method 9B FS 5970
Temperature resistance 适应温度	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	DIN EN 1876-2 BS 3424 Method 10 FS 5874
Flammability (optional) 防火 (可选)	B1 M2 NFPA-701 ASTM E84	NFPA-701 ASTM E84 NFPA-701	B1 M2 NFPA-701 ASTM E84	B1 M2 NFPA-701 ASTM E84	
Application 用途	Inflatables 充气材料	Inflatables 充气材料	Inflatables 充气材料	Inflatables 充气材料	

All our technical characteristics are indicative

以上参数如有变动，恕不另行通知。