

卡车侧帘布

Item 货号	C 6000L PANAMA	C 7119 L	C 8000 L	C 9000 L	Testing Method
Width 门幅	250 - 320 cm 98.4 - 126 inch	150 - 320 cm 59 - 126 inch	250 - 320 cm 98.4 - 126 inch	250 - 320 cm 98.4 - 126 inch	
Base Fabric 基布	100%PES Panama 1100Dtex 15*15/inch	100%PES woven 1100Dtex 18x18/inch	100%PES woven 1100Dtex 20x20/inch	100%PES woven 1100Dtex 23*23/inch	DIN EN ISO 2060
Total Weight 总克重	900 g/m ² 26.5 OZ/YD ²	630 g/m ² 18.5 OZ/YD ²	650 g/m ² 19 OZ/YD ²	680 g/m ² 20 OZ/YD ²	DIN EN ISO 2286-2 BS 3424 Method 5A
Composition Fabric 基布克重	260 g/m ² 7.6 OZ/YD ²	160 g/m ² 4.7 OZ/YD ²	180 g/m ² 5.3 OZ/YD ²	200 g/m ² 5.9 OZ/YD ²	DIN EN ISO 2286-2 BS 3424 Method 5B
Composition Coating 涂层克重	640 g/m ² 18.9 OZ/YD ²	470 g/m ² 13.8 OZ/YD ²	470 g/m ² 13.7 OZ/YD ²	480 g/m ² 14.1 OZ/YD ²	
Lacquering (Optional) 表处 (可选)	Gloss Acrylic 1/1	Gloss Acrylic 1/1	Gloss Acrylic 1/1	Gloss Acrylic 1/1	
Breaking Strength Warp 抗拉强度 (经向)	4000 N/5cm 900 LBS/2inch	2200 N/5cm 495 LBS/2inch	2500 N/5cm 560 LBS/2inch	3000 N/5cm 675 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Breaking Strength Weft 抗拉强度 (纬向)	3500 N/5cm 788 LBS/2inch	1800 N/5cm 405 LBS/2inch	2300 N/5cm 518 LBS/2inch	2800 N/5cm 630 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Tear Strength Warp 撕裂强度 (经向)	600 N 135 LBS	250 N 56 LBS	270 N 60 LBS	300 N 67 LBS	DIN 53 363 BS 3424 Method FS 5134
Tear Strength Weft 撕裂强度 (纬向)	500 N 112 LBS	250 N 56 LBS	250 N 56 LBS	300 N 67 LBS	DIN 53 363 BS 3424 Method FS 5134
Adhesion 剥离强度	100 N/5cm 22.5 LBS/2inch	100 N/5cm 22.5 LBS/2inch	100 N/5cm 22.5 LBS/2inch	100 N/5cm 22.5 LBS/2inch	DIN 53 357 BS 3424 Method 9B FS 5970
Temperature resistance 适应温度	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	DIN EN 1876-2 BS 3424 Method 10 FS 5874
Flammability (optional) 防火 (可选)	M2 B1 NFPA-701 ASTM E84 CSFM	M2 B1 NFPA-701 ASTM E84 CSFM	M2 B1 NFPA-701 ASTM E84 CSFM	M2 B1 NFPA-701 ASTM E84 CSFM	
Application 用途	Side Curtains 卡车侧帘布	Side Curtains 卡车侧帘布	Side Curtains 卡车侧帘布	Side Curtains 卡车侧帘布	

All our technical characteristics are indicative

以上参数如有变动，恕不另行通知。