

## 篷房材料

Item 货号	650克 篷房	750克 包边布篷房	750克 遮光篷房	850克 遮光篷房	Testing Method
Width 门幅	250 - 300 CM 98.4 - 118 inch	150 CM 59 inch	250 - 300 CM 98.4 - 118 inch	250 - 300 CM 98.4 - 118 inch	
Base Fabric 基布	100%PES 1100Dtex 20*20/inch	100%PES Panama 1100Dtex 15*15/inch	100%PES 1100 Dtex 23*23/inch	100%PES 1100 Dtex 23*23/inch	DIN EN ISO 2060
Total Weight 总克重	650 g/m <sup>2</sup>	750 g/m <sup>2</sup>	750 g/m <sup>2</sup>	850 g/m <sup>2</sup>	DIN EN ISO 2286-2 BS 3424 Method 5A
Composition Fabric 基布克重	19 OZ/YD <sup>2</sup> 200 g/m <sup>2</sup>	22 OZ/YD <sup>2</sup> 260 g/m <sup>2</sup>	22 OZ/YD <sup>2</sup> 200 g/m <sup>2</sup>	25 OZ/YD <sup>2</sup> 200 g/m <sup>2</sup>	DIN EN ISO 2286-2 BS 3424 Method 5B
Composition Coating 涂层克重	6 OZ/YD <sup>2</sup> 450 g/m <sup>2</sup> 13 OZ/YD <sup>2</sup>	7.6 OZ/YD <sup>2</sup> 490 g/m <sup>2</sup> 14.4 OZ/YD <sup>2</sup>	6 OZ/YD <sup>2</sup> 550 g/m <sup>2</sup> 16 OZ/YD <sup>2</sup>	6 OZ/YD <sup>2</sup> 650 g/m <sup>2</sup> 19 OZ/YD <sup>2</sup>	
Lacquering (Optional) 表处 (可选)	PVDF Acrylic	Acrylic	PVDF Acrylic	PVDF Acrylic	
Breaking Strength Warp 抗拉强度 (经向)	2600 N/5cm	4000 N/5cm	3000 N/5cm	3200 N/5cm	DIN 53 354 BS 3424 Method
Breaking Strength Weft 抗拉强度 (纬向)	585 LBS/2inch 2400 N/5cm	900 LBS/2inch 3600 N/5cm	675 LBS/2inch 2800 N/5cm	720 LBS/2inch 3000 N/5cm	FS 5100 DIN 53 354 BS 3424 Method
Tear Strength Warp 撕裂强度 (经向)	540 LBS/2inch 250 N	810 LBS/2inch 500 N	630 LBS/2inch 300 N	675 LBS/2inch 300 N	FS 5100 DIN 53 363 BS 3424 Method
Tear Strength Weft 撕裂强度 (纬向)	56 LBS 250 N	112 LBS 500 N	67 LBS 260 N	67 LBS 260 N	FS 5134 DIN 53 363 BS 3424 Method
Adhesion 剥离强度	56 LBS 120 N/5cm 27 LBS/2inch	112 LBS 120 N/5cm 27 LBS/2inch	58 LBS 120 N/5cm 27 LBS/2inch	58 LBS 120 N/5cm 27 LBS/2inch	FS 5134 DIN 53 357 BS 3424 Method 9B FS 5970
Temperature resistance 适应温度	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	DIN EN 1876-2 BS 3424 Method 10 FS 5874
Flammability (optional) 防火 (可选)	EN13501 B1 M2 NFPA-701 ASTM E84	EN13501 B1 M2 NFPA-701 ASTM E84	EN13501 B1 M2 NFPA-701 ASTM E84	EN13501 B1 M2 NFPA-701 ASTM E84	
Application 用途	Tents 篷房材料	Tents 篷房材料	Tents 篷房材料	Tents 篷房材料	

All our technical characteristics are indicative

以上参数如有变动，恕不另行通知。