

卡车篷布

Item 货号	U4061M	U2261M	U1861M	U1461M	Testing Method
Width 门幅	155 cm 61 inch	155 cm 61 inch	155 cm 61 inch	155 cm 61 inch	
Base Fabric 基布	100%PES 1650Dtex 16x16/inch	100%PES 1650Dtex 18x17/inch	100%PES 1100Dtex 18x17/inch	100%PES 1100Dtex 20x20/inch	DIN EN ISO 2060
Total Weight 总克重	1355 g/m ² 40 OZ/YD ²	745 g/m ² 22 OZ/YD ²	610 g/m ² 18 OZ/YD ²	475 g/m ² 14 OZ/YD ²	DIN EN ISO 2286-2 BS 3424 Method 5A
Composition Fabric 基布克重	420 g/m ²	210 g/m ²	180 g/m ²	180 g/m ²	DIN EN ISO 2286-2 BS 3424 Method 5B
Composition Coating 涂层克重	12.4 OZ/YD ² 935 g/m ² 27.6 OZ/YD ²	6.2 OZ/YD ² 535 g/m ² 15.8 OZ/YD ²	5.3 OZ/YD ² 430 g/m ² 12.7 OZ/YD ²	5.3 OZ/YD ² 295 g/m ² 8.7 OZ/YD ²	
Lacquering (Optional) 表处 (可选)	Matte	Matte	Matte	Matte	
Breaking Strength Warp 抗拉强度 (经向)	6500 N/5cm 1460 LBS/2inch	3000 N/5cm 670 LBS/2inch	2800 N/5cm 630 LBS/2inch	2400 N/5cm 540 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Breaking Strength Weft 抗拉强度 (纬向)	6000 N/5cm 1350 LBS/2inch	2800 N/5cm 630 LBS/2inch	2600 N/5cm 585 LBS/2inch	2200 N/5cm 500 LBS/2inch	DIN 53 354 BS 3424 Method FS 5100
Tear Strength Warp 撕裂强度 (经向)	1300 N 290 LBS	650 N 145 LBS	500 N 110 LBS	250 N 56 LBS	DIN 53 363 BS 3424 Method FS 5134
Tear Strength Weft 撕裂强度 (纬向)	1300 N 290 LBS	600 N 135 LBS	450 N 100 LBS	250 N 56 LBS	DIN 53 363 BS 3424 Method FS 5134
Adhesion 剥离强度	170 N/5cm 38 LBS/2inch	120 N/5cm 27 LBS/2inch	120 N/5cm 27 LBS/2inch	120 N/5cm 27 LBS/2inch	DIN 53 357 BS 3424 Method 9B FS 5970
Temperature resistance 适应温度	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	-30°C/+70°C	DIN EN 1876-2 BS 3424 Method 10 FS 5874
Flammability (optional) 防火 (可选)	ASTM E84 CSFM NFPA-701	ASTM E84 CSFM NFPA-701	ASTM E84 CSFM NFPA-701	NFPA-701	
Application 用途	Truck Cover 卡车篷布	Truck Cover 卡车篷布	Truck Cover 卡车篷布	Truck Cover 卡车篷布	

All our technical characteristics are indicative

以上参数如有变动，恕不另行通知。