



PRODUCT INFORMATION

senosan® aqua
senosan® metaliX aqua

PRODUCT

Multilayer composite made of a main extrusion HI-ABS layer and a co-extruded high gloss, good chemical and stress-cracking resistant, impact modified and UV-resistant PMMA top layer and easyglide® rear side.

PROPERTIES | ADVANTAGES

- good chemical resistance
- excellent thermoformability

TECHNICAL PROPERTIES

Property	Value
Density	1.12 – 1.16g/cm ³
Tensile E-Modulus	2 100 MPa
HDT-A / 1.82 MPa	100°C

PRODUCT DETAILS

CO-EX

senosan® aqua

uni colour white 11119

senosan® metaliX aqua

metallic colour white 1889/pearl 11120

Thickness: 4.6 – 11.0 mm

Width: up to 2,600 mm

With regard to deliveries of oversized sheets, we kindly ask you to contact us separately concerning transport option and prices.

Colours: uni, metallic

Surface: smooth, high gloss

Min. Order: 5 t per colour and thickness
(1 t per sheet size)

Note:

In order to achieve sufficient UV protection the minimum thickness of a thermoformed spa/hot tub should not be less than 1.7 mm residual wall thickness.

PRICE

On request.

POSSIBLE APPLICATIONS

Spas, hot tubs