SEALON KOREA

5376 DECO FILM (7 SKU)

CATEGORY	Solid	Reflective-Stretch	Reflective-Non	Silicone	Hairline	Embossed	FABRIC(DT-001)
COMPOSITION	Polyurethane	Polyurethane	Polyurethane	Silicone	Polyurethane	Polyurethane	Polyamide, Polyurethane
CHARACTERISTIC	Matte solid	Stretchable Reflective	Reflective	Non-Slip, Strong migration	Texture appearance	Texture appearance	Fabric
NORMAL THICKNESS	0.10mm (±0.02mm)	0.15~0.2mm (±0.02mm)	0.15~0.2mm (±0.02mm)	0.15, 0.30, 0.50mm (±0.02mm)	0.15 & 0.25mm (±0.02mm)	0.20~0.50mm (±0.02mm)	0.35mm (±0.02mm)
WIDTH	500mm,Custom Size	500mm,Custom Size	500mm,Custom Size	500mm,Custom Size	500mm,Custom Size	500mm,Custom Size	1,420mm,Custom Size
CARRIER	PE or OPP(Inner), PET(Outer)	PE or OPP(Inner), PET(Outer)	PE or OPP(Inner), PET(Outer)	PE or OPP(Inner), PET(Outer)	PE or OPP(Inner), PET(Outer)	PE or OPP(Inner),Release paper(Outer)	None
GLUE LINE TEMPERATURE RANGE (°C)	113~181°C	113~181°C	113~181°C	113~181°C	113~181°C	113~181°C	113~181°C
SOFTENING POINT	80.5°C	80.5°C	80.5°C	80.5°C	80.5°C	80.5°C	80.5°C
WORKING CONDITION (°C)	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa	140~170°C 10~30sec 0.4~0.5MPa
ABRASION RESISTANCE	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
STORAGE	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)	Below 25°C, Avoid High Humidity (<60%)